

验报告

TEST REPORT

中心编号(No.): 201705BW140

样品名称:

挤塑板

Sample Name

委托单位:

北京大友丰业工贸有限公司

Client

检验类别:

委托检验

Test Type

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

出心獨与(1)	0.): 201705BW140	大きなななから	1页 共2页			
样品名称	機嫌ないままままま	检验类别	委托检验			
委托单位	北京大友丰业工贸有限公司	公 商品标				
生产单位	北京大友丰业工贸有限公司	等一级				
生产日期		样品编号				
来样日期	2017年 05月 15月	规格型号	X150			
样品数量	123 m 2 1 1 2 1 2 1 2 1 2 1 2 1 2 1 2 1 2 1	样品状态	THE PERSONAL PROPERTY OF THE PERSONAL PROPERTY			
检验依据	GB/T 10801.2-2002《绝热用挤塑聚苯乙烯泡沫塑料(XPS)》 GB 8624-2012《建筑材料及制品燃烧性能分级》					
检验项目	1. 压缩强度 2. 吸水率 3. 绝热性能 (导热系数) 4. 尺寸稳定性 5. 燃烧性能等级 6. 外观质量					
检验结论	*经检验,送检样品的压缩强度 寸稳定性、外观质量的检验结果符合的技术指标要求;燃烧性能等级的机 板状建筑材料及制品B2(E)级的机	会标准 GB/T 10801 会验结果符合标准 G 支术指标要求。* 签发日期: 2017	2-2002 中 X150 型 B 8624-2012 中平 年 05 月 25 日			
			金验测试章)			
备注:(此处	\$47 \$47 \$45 \$45 \$45 \$45 \$45 \$45 \$45 \$45 \$45 \$45		2002			

批

制:

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201705BW140

第2页共2页

序号	检验项目		标准要求 (X150型)	检验结果	单项结论
	压缩强度/kPa		25° \$15° \$15° \$15° \$15° \$15° \$15° \$15° \$1	2218	
	吸水率(浸水·96h)/%			0.80	3
	绝 热 导热系数	10.6	≤0.028	0.027	
	性 [W/(m·K)] 25°C	0.030	0.029		
	尺寸稳定性 (70℃±2℃下,48h) /%		2.0		
	高级在全身不足	的熔 度/mm	150 150 150	77 136 74 136 74	
	性能 数 低落	7燃烧 切引燃 .现象	无 引燃波纸现象	无引燃滤纸现象	
	B2级 氧指数位	1967	26°32°4	26.6	108 000
	大型 ·		表面平整, 无夹杂物, 颜色均匀。不应有明显影响使用的可见缺陷, 如起泡、製口、变形等	表面乎整,无央 杂物,颜色均 匀。无可见缺陷	**************************************

备注:燃烧性能等级:本试验结果只与制品的试样在特定试样条件下的性能相关,不 能作为评价该制品在实际使用中潜在火灾危险性的唯一依据。

说。明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。 This test report is invalid without the signatures of the related persons.
- 3. 本报告涂改、部分复印无效。 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议、应于收到报告之目起土五个工作日内向本中心提出、逾土期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

50 委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任曲建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code): 100024

电话(TeD: (010) 51164723 51164718

传真(Fax)。(010) 51164724

报告真伪查询(Tel):(010)51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱(E-mail): dmtc2007@163.com



