

检验报告

TEST REPORT

中心编号(No.): 201704DW166




样品名称:	内墙乳胶漆			
Sample Name				
委托单位:	北京云城涂料厂			
Client				
检验类别:	委托检验			
Test Type				

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201704DW166			第1页 共2页		
样品名称	内墙乳胶漆		检验类别	委托检验	
委托单位	北京云城涂料厂		商标	建筑	
生产单位	北京云城涂料厂	建建建筑	等级	二条品 了	
生产日期		認認	样品编号	認館	
来样日期	2017年04月19日	SHERK	规格型号	究起紀	
样品数量	3kg	THE STATES	样品状态	液态	
检验依据	GB/T 9756-2009《合成树脂乳液内墙涂料》				
检验项目	1. 施工性	2. 对比率	表表。 25222	耐洗刷性	
检验结论	*经检验,送检料 准 GB/T 9756-2009 中	内墙面漆(一等。	之日期: 201	7年05月25日	
备注:(此处	THE THE THE	知能	967 TO-C	检验测试章)	
			结结	的地方,	

检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

制:

邮编:/100024

准:

批

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201704DW166

第2页 共2页

序号	检验项目	标准要求 (一等品)	检验结果	单项结论
遊	浅工性	刷涂二道无障碍	刷涂二道无障碍	符合
2	对比率(白色和浅色)	≥0.93	0.93	合格
335	耐洗刷性/次	≥1000	1000	合格

备注: (此处空白)

说 明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话(Tel):(010)51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com