



# 检验损告

TEST REPORT

中心编号(No.): 201706AW159

Sample Name

委托单位: 三河市隆泽建材销售有限公司

Client

检验类别。

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







(国家)建筑材料工业技术监督研究中心

#### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201706AW159

		ロナエロナエロ	无 小 从 六 4 火	
样品名称	松果料连领和块 2	检验类别	<b>秦托检验</b> 2000年	
委托单位	三河市隆泽建材销售有限公司	商品标		
生产单位	三河市隆泽建材销售有限公司	等。级	MU5.0	
生产日期		样品编号		
来样日期	2017年06月07日	规格型号	395mm×190mm×195mm	
样品数量		样品状态		
检验依据	GB/T 15229-2014《轻集料混凝出小型室心砌块》			
检验项目	138度等級 1-22-50-50-50-50-50-50-50-50-50-50-50-50-50-			
检验结论	*经检验,送检样品的密度等级的检验结果符合标准 GB/T 15229-2011中密度等级 1200 级的技术指标要求:抗压强度的检验结果符合标准 GB/T 15229-2011 中强度等级 MU5.0 的技术指标要求。*			
	签发日期: 2017年06月14日			
	全年中华中华中华中华中华中华中华中华中华中华中华中华中华中华中华中华中华中华中华			
备注:《此》			學验服成中心 理學與专用章	

制:节、

#### (国家) 建筑材料工业技术监督研究中心

#### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

#### 验报告

TEST REPORT

中心编号(No.): 201706AW159

第2页共2页

序号  检验项目	标准要求	检验结果	单项结论
室度等级/(kg/r (密度等级/1200	n) ≥1110, ≤1200	1170	
抗压强度/MP		平均值量小	ATTITULE
人。 (强度等级MUS	5.00 ≥4.0	5.2 5.0	

(以下空白)

备注:(此处空白)

### 说。公明

#### Notice

- I、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
  This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
  This test report is invalid if erased, altered or copied partially.
- 4. 对本报告者有异议,应于收到报告之日起中五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 51 委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张、复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管底东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code): 100024

电话(Tel);(010)51164723 51164718

传真(Fax)。(010)51164724

报告真伪查询(Tel):(010)51164716

网址(Web): http://www.dnitc.org.cn/

电子邮箱(E-mail): dmtc2007@163.com

