



检验报告

TEST REPORT

中心编号(No.): 201605AW229

样品名称: 复合轻集料混凝土
Sample Name
委托单位: 北京京盛泰达建材有限公司
Client

检验类别: 委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201605AW229	第1页共2页				
样品名称	复合轻集料混凝土	检验类别	委托检验 000000000000000000000000000000000000			
委托单位	北京京盛泰达建林有限公司	商标				
生产单位	北京京盛泰达建材有限公司	等级	经经验程			
生产日期	理觀鏡語	样品编号	胡起語			
来样日期	2016年05月20日	规格型号				
样品数量	14 時時時	样品状态	块状, 外观完好			
检验依据	GB/T 20473-2006《建筑保温砂浆》 JGJ 51-2002《轻骨料混凝土技术规程》					
检验项目	1. 杭压强度 2. 干密度					
检验结论	*依据标准 JGJ 51-2002、GB/T 20473-2006 規定的试验方法进行检验,送检样品的抗压强度、干密度的检验结果见第 2 页。* 签发日期: 2016 年 05 月 30 日 (检验测试章)					
备注:(此处空白)			CHAD Y			

准: 批

核:

检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201605AW229

第2页共2页

序号	检验项目	标准要求	检验结果	单项结论
	抗压强度/MPa		7.5	100
2	千密度/ (kg/m³)		1500	和智能

(以下空白)

备注: (1) 抗压强度试验依据标准 JGJ 51-2002 规定的试验方法进行检验;

(2) 干密度试验依据标准 GB/T 20473-2006 规定的试验方法进行检验。

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

网址 (Web): http://www.dmte.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com