

# 检验报告

TEST REPORT


中心编号(No.): 201607BW183

样品名称:	内墙耐水腻子粉		
Sample Name			
委托单位: Client	江苏雄鹰建材科技有限公司		
检验类别:	委托检验		

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortan





## 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201607BW183

第1页共2页

			6 1 X X Z X			
样品名称	内墙耐水腻子粉	检验类别	委托检验			
委托单位	江苏雄鹰建材科技有限公司	商。标	家家安 雅思美			
生产单位	江苏雄鹰建材科技有限公司	等级				
生产日期		样品编号	認調			
来样日期	2016年07月22日	规格型号	XY-SN-NR-1			
样品数量	25kg	样品状态	粉状			
检验依据	JG/T 298-2010《建筑室内用腻子》	43844	超级			
检验项目	1. 容器中状态 2. 施工性 3. 干燥时间 4. 初期干燥抗裂性 5. 打磨性 6. 耐水性 7. 粘结强度					
检验结论	*经检验,送检样品的容器中状态、施工性、干燥时间、初期干燥抗裂性、打磨性、耐水性、粘结强度的检验结果符合标准 JG/T 298-2010 中耐水型(N)的技术指标要求。*					
語程		发日期: 2016年 (检验	08月15日			
备注:(此处	室白)		<b>企</b> 验			

批 准: 制:

检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723





#### (国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201607BW183

第2页共2页

序号	检验项目		标准要求 耐水型(N)	检验结果	单项结论	
i	容	器中状态		无结块、均匀	无结块、均匀	符合
2	施工性			刮涂无障碍	刮涂无障碍	符合
		时间 单道施工 (表干) 厚度/mm	<2	€2	0.5	合格
3			≥2	≤5	0.8	合格
4	初期干燥抗裂性 (3h)		无裂纹	无裂纹	符合	
5		打磨性		手工可打磨	手工可打磨	符合
6	耐水性		48h 无起泡、开 裂及明显掉粉	无异常	符合	
7	粘结强度 /MPa	标准状	态	>0.50	0.67	合格
		浸水后		>0.30	0.44	合格

(以下空白)

备注: (1) 配比: 粉:水=1.0:0.34;

(2) pH 值: 12.0。

7677477

#### 说明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
  This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
  This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
  This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com

