



检验报告

TEST REPORT

中心编号(No.): 201608DW003



样品名称:	干混地面砂浆
Sample Name	
委托单位: Client	香河明远新型环保建材有限公司
检验类别:	大学·罗···································

2-112-1-12-1-12-1-1

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar


位のマルチ





Test Type





建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201608DW003

第1页共2页

1	201000		コーンベーノベーンベー			
样品名称	干混地面砂浆	检验类别	委托检验			
委托单位	香河明远新型环保建材有限公司	商标	香塔			
生产单位	香河明远新型环保建材有限公司	等级	語語語			
生产日期	2016年07月25日	样品编号	0009			
来样日期	2016年08月03日	规格型号	M7.5			
样品数量	20kg	样品状态	粉状			
检验依据	GB/T 25181-2010《预拌砂浆》					
检验项目	1. 保水率 2. 凝结时间 3. 2h 稠度损失率 4. 28d 抗压强度					
检验结论	*依据标准 GB/T 25181-2010 规定的试验方法进行检验,送检验保水率、凝结时间、2h 稠度损失率、28d 抗压强度的检验结果见第** 验结论 签发日期: 2016年 094月					

备注: (此处空白)

批准:



检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201608DW003

第2页共2页

序号	检验项目	标准要求	检验结果	单项结论
額	保水率/%		96.4	THE THE
2	凝结时间/h	328635	3.3	野島和
33	2h 稠度损失率/%	的思想	28,7	
54 2	28d 抗压强度/MPa	DELE	9.4	

(以下空白)

备注: 配比: 粉:水=1.0:0.14。

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com

