

150002283084



# 检验报告

TEST REPORT

中心编号(No.): 201701AW040

样品名称:

Sample Name

委托单位:北京通达利建筑材料厂

Client

Test Type

(国家)建筑材料工业技术监督研究中心,

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



(国家)建筑材料工业技术监督研究中心

# 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

#### 检 验报告

REPORT TEST

中心编号(No.): 201701AW040

THE TOTAL SECTION OF THE PARTY		サイトサインというからす		
样品名称	· · · · · · · · · · · · · · · · · · ·	检验类别	秦托检验 25	
委托单位	北京通达利建筑林科	商品标		
生产单位	北京通达利建筑材料厂	等。级		
生产日期		样品编号		
来样日期	2017年01月20日	规格型号		
样品数量		样品状态		
检验依据	JG/T/298-2010《建筑室两册献子》			
检验项目。	中,初期开煤坑製作(3h) 22 粘结磁度			
4564 <b>%</b> 4654	*经检验,送检样品的初期干燥与符合标准1G/T 298-2010 中耐水型(N	)的技术指标要 期: 2017年		
<b>备注: (此处文的)</b>				

批准:

核: 7

检验单位地址:北京市朝阳区管庄中国建林院内北楼〇

电话: 010-51164723 邮編: 0100024

# (国家)建筑材料工业技术监督研究中心

# 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

TEST REPORT

中心编号(No.): 201701AW040

第2页共2页

原是	检验项目	标准要求 [耐水型(N)]	检验结果	单项结论
	初期干燥抗裂性(3H)			
	粘结强度,标准状态	20.50		
	MPa Tokker	>0.30	032	

备注:(1)配比:粉:水=1.0:0.40;

(2) pH 值=10.0。

#### 说 明

### Notice

- 1、本报告无中心广检验测试章",和骑缝章无效 This test report is invalid without the seal.
- 本报告无"编制、审核、一批准"。签字无效。 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

- 去。对本报告若有异议,应于收到报告之日起中五个工作日内向本中心提出,通 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托太提供,一中心不对真实性负责,委托检验结 果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伤纸张,复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code):100024

电话(Tel):(010)51164723-51164718

传真(Fax):(010)51164724

报告真伪查询(Tel):(010) 51164716

Web): http://www.dmte.org.cn/

电子邮箱(E-mail): dmte2007a163.com

