



检验报告

TEST REPORT

中心编号(No.): 201609AW186



件而名称:	LAOPING DLK 针刺毯 TAPITA
Sample Name	
委托单位:	北京航宇海纳防火保温建材有限公司
Client	

Test Type

检验类别:

(国家) 建筑材料工业技术监督研究中心

建筑材料正业于混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201609AW186

第1页共2页

			フェン・フィン		
样品名称	DLK针刺毯	检验类别	委托检验		
委托单位	北京航宇海纳防火保温建材有限公司	商标	航字		
生产单位	北京航宇海纳防火保温建材有限公司	等级	型認定		
生产日期		样品编号	招望程		
来样日期	2016年09月19日	规格型号	序20mm		
样品数量		样品状态	块状		
检验依据	GB/T 18696.2-2002《声学 阻抗管中吸声系数与声阻抗的测量 第2部分: 传递函数法》 GB/T 25998-2010《矿物棉装饰吸声板》				
检验项目	1.降噪系数(阻抗管法)				
依据标准 GB/T 18696.2-2002 规定的试验方法进行检验,送标降噪系数 (阻抗管法) 的检验结果符合标准 GB/T 25998-2010 中于技术指标要求。					
	09.月 26日				
备注:(此处空白) 台灣 自然			企服 专用章		

此准是如何之审核: 光京

编制: 长亮



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201609AW186

第2页共2页

序号	检验项目	标准要求 (千法板)	检验结果	单项结论
	降噪系数 (阻抗管法)	≥0.30	0.32	合格

(以下空白)

国的对话或

备注:(此处空白)



说明

Notice

- 本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>dmtc2007@163.com</u>