



检验报告

TEST REPORT

中心编号(No.): 201607AW150


THIT

样品名称:	轻型料多孔砖			
Sample Name				
委托单位: Client	北京天盛华星新型建材有限公司			
检验类别: Test Type	委托检验			

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Conter for Quality Supervision and Test of Dry-mixed Mortar





建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告


TEST REPORT

中心编号(No.): 201607AW150

第1页共2页

备注:(此处空白)		全经验测量					
检验结论	*依据标准 GB/T 15229-2011 规定的试验方法进行检验,送检样品的密度等级、抗压强度的检验结果见第 2 页。* 签发日期: 2016 年 08 月 03 日 (检验测试章)						
检验 <mark>项目</mark>	1. 密度等级 2. 抗压强度						
检验依据	GB/T 15229-2011《轻集料混凝土小型空心砌块》						
样品数量	10块子品品品	样品状态	块状子子子子子				
来样日期	2016年07月25日	规格型号	190mm×90mm×53mm				
生产日期	混乱经验是	样品编号					
生产单位	北京天盛华星新型建材有限公司	等级	MU5.0				
委托单位	北京天盛华星新型建材有限公司	商标					
样品名称	轻型料多孔砖	检验类别	委托检验				

批准: (



电话: 010-51164723

邮编: 100024



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201607AW150

第2页 共2页

序号	检验项目	标准要求		检验结果		单项结论
	密度等级/ (kg/m³)			1180		
2 抗压强度/MPa	拉压器度AADa	平均值	最小值	平均值	最小值	建超
	SCALE SERVICE	語		5.1	4.8	

(以下空白)

备注: (此处空白)

说明

Notice

1、本报告无中心"检验测试章"和骑缝章无效。

This test report is invalid without the seal.

2、本报告无"编制、审核、批准"签字无效。

This test report is invalid without the signatures of the related persons.

3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com