



# 检验报告

#### TEST REPORT

中心编号(No.): 201612EW104

TIMIC

样品名称:	B型干拌复合轻集料混凝土
Sample Name	
委托单位:	北京万达天成科技有限公司
Client	
检验类别:	委托检验
Test Type	

建筑材料工业技术监督研究中心
Technical Supervision and Research Center of the Building Materials Industry





### 建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

150002283084

## 检验报告

TEST REPORT

中心编号(No.): 201612EW104

第1页共2页

			1 1 7 7 4 1				
样品名称	B型干拌复合轻集料混凝土	检验类别	委托检验				
委托单位	北京万达天成科技有限公司	商标	铭辉建冶				
生产单位	北京万达天成科技有限公司	等级					
生产日期	2016年11月27日	样品编号					
来样日期	2016年12月27日	规格型号	100mm×100mm× 100mm				
样品数量	35 块	样品状态	块状				
检验依据	JG/T 266-2011《泡沫混凝土》						
检验项目	1. 干密度 2. 导热系数 3. 强度等级						
检验结论	*经检验,送检样品的干密度 JG/T 266-2011 中 A08 级的技术指标 JG/T 266-2011 中 C3 级的技术指标要求	:要求: 强度等级的表。* 注日期: 2017年 检验	企验结果符合标准 拉术发表 01月09日 测试章 2週专用章				

备注:(此处空白)

肚准: 多种人工 核: 水水 编 ;

编制:分



## 建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

## 检验报告

TEST REPORT

中心编号(No.): 201612EW104

第2页 共2页

727	ATTENDED TO LANGE TO SUITE TO					
序号	检验项目	标准要求		检验结果		单项结论
1	千密度(A08 级)/(kg/m³)	≤800 (容许误差+5%) ≤0.21		796 0.19 (平均温度: 25.00℃)		合格合格
2	导热系数(A08 级) /[W/(m·K)]					
3	强度等级(C3 级)/MPa	每组 平均值	单块 最小值	每组 平均值	单块 最小值	合格
		≥3.00	≥ 2.550	3.14	2.985	

(以下空白)

备注: (此处空白)

邮编: 100024

#### 说 明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
   This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
  This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



大田二