



检验报告

TEST REPORT

中心编号(No.): 201703DW123

样品名称:	气泡混合轻质土
Sample Name	
委托单位: Client	重庆发正建筑材料有限公司
检验类别: Test Type	委托检验

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703DW123

第1页共2页

	201703D W125	70	1 火 共 2 火			
样品名称	气泡混合轻质土	检验类别	委托检验			
委托单位	重庆发正建筑材料有限公司	商标	相思			
生产单位	重庆发正建筑材料有限公司	等级	CF10			
生产日期	2017年02月	样品编号	罗拉克			
来样日期	2017年03月21日	规格型号	100mm×100mm ×100mm			
样品数量	3 4 1 2 2 3 3 4 3 5 5	样品状态	块状			
检验依据	CJJ/T 177-2012《气泡混合轻质土填筑工程技术规程》					
检验项目	1. 抗压强度					
检验结论	*经检验,送检样品的抗压强度的检验结果符合标准 CJJ/T 177-2012 中强度等级 CF10 的技术指标要求。*					
		签发日期: 2017	年 03 月 28 日 金验测试章》			

备注: (此处空白)

批准:

审核: 34.7

编制:為公

检验单位地位

北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703DW123

第2页共2页

序号	检验项目		标准要求 (CF10)	检验结果	单项结论
137	抗压强度	每组平均值	≥10.00	10.30	合格
亞	/MPa	每块最小值	≥8.50	9.62	合格

(以下空白),

备注:(此处空白)

说明

Notice

- 本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report,
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com