



检验报告

TEST REPORT

中心编号(No.): 201704AW141




Sample Name	
委托单位:	河北美斯德保温材料有限公司
Client	
松心米印	

Test Type

样品名称.

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry mixed Mortar





1500022830国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(N	0.): 201	704AW141
--------	----------	----------

第1页共2页

5-13-5	10.): 201/04/11/141	MATIN.	* 17 7 7 2 W		
样品名称	玻璃棉卷毡	检验类别	委托检验		
委托单位	河北美斯德保温材料有限公司	商标			
生产单位	河北美斯德保温材料有限公司	等级			
生产日期		样品编号			
来样日期	2017年04月11日	规格型号	10000mm×1200mm×70mm		
样品数量		样品状态			
检验依据	GB/T 13350-2008《绝热用玻璃棉及其制品》				
检验项目	1. 密度 2. 导热系数 3. 燃烧性能				
	*经检验,送检样品的密度、 准 GB/T 13350-2008 中毡的密度				
检验结论		发日期: 20	017年04月19日 (检验测试章)		

备注:(此处空白)

t 准: 多加 工 审核: 送水 、编制: 苏亮

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201704AW141

第2页共2页

序号	检验项目	标准要求 (毡的密度 10kg/m³)	检验结果	单项结论
遊	密度,kg/m³	10 +20%	9.2	26 A
132	导热系数(平均温度 70 ½°C) /[W/ (m·K)]	≤0.062	0.061 (平均温 度 70.00℃)	2 6 8 C
133	燃烧性能	大大		

(以下空白)

备注:燃烧性能试验结果只与制品的试样在特定试验条件下的性能相关,不能作为评价 该制品在实际使用中潜在火灾危险性的唯一依据。

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.en/

电子邮箱 (E-mail): dmtc2007@163.com