



检验报告

TEST REPORT

中心编号(No.): 201612AW116

超過程的

样品名称:	粘结砂浆 计
Sample Name	
委托单位:	北京芳业达建材有限公司
检验类别:	委托检验

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





150002283084 (国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.):	201612AW11	6
------------	------------	---

第1页共2页

	.c.y. 201012711110	7	火 共 4 火		
样品名称	粘结砂浆 5000000000000000000000000000000000000	检验类别	委托检验		
委托单位	北京芳业达建材有限公司	商标	超超		
生产单位	北京芳业达建材有限公司	等级	建筑		
生产日期	经的程度的	样品编号			
来样日期	2016年12月06日	规格型号	干粉型		
样品数量	20kg	样品状态	粉状		
检验依据	JGJ 144-2004《外墙外保温工程技术规程》 DB11/T 584-2013《保温板薄抹灰外墙外保温施工技术规程》				
检验项目	1. 拉伸粘结强度(与模塑板) 2. 拉伸粘结强度(与挤塑板) 3. 拉伸粘结强度(与水泥砂浆) 4. 可操作时间				
检验结论	*依据标准 JGJ 144-2004 规定目的检验结果符合标准 DB11/T 584	的试验方法进行检验, 4-2013 中胶粘剂的技术	送检样品所检项 治标要求。*		
	签数	过日期: 2017年 02 (检验测	The state of the s		
备注:(此处	室町 2002年11日	124C	1111		

奋注:(此处空台)

批准: 0

宙 核.

龙机

编制: 书意

检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



建筑材料工业技术监督研究中心

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201612AW116

第2页 共2页

序号	检验项目		检验项目 (胶粘剂)	检验结果 单项结论	
拉伸粘结强度 1 (与模塑板)	结结结	常温常态	≥0.10	0.12	合格
	浸水 48h, 干燥 2h	≥0.06	0.07	合格	
To the second	MPa	浸水 48h, 干燥 7d	≥0.10	011	合格
拉伸粘结强度 2 (与挤塑板) /MPa	常温常态	≥0.20	0.23	合格	
	浸水 48h, 干燥 2h	≥0.10	0.15	合格	
	浸水 48h, 干燥 7d	≥0.20	0.21	合格	
	常温常态	≥0.6	0.9	合格	
3	拉伸粘结强度 (与水泥砂浆) /MPa	浸水 48h, 干燥 2h	≥0.3	0.5	合格
E P		浸水 48h, 于燥 7d	≥0.6	0.7	合格
4	可操作时间/h		1.5~4.0	2.0	合格

(以下空白)

备注: (1) 配比: 粉:水=4:1:

(2) 模塑板规格: 18kg/m³; 挤塑板规格: 32kg/m³。

说明

Notice

- 人 本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真(Fax):(010)51164724

报告真伪查询 (Tel): (010) 51164716

网址(Web):http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com