



检验报告

TEST REPORT

中心编号(No.): 201703DW103

样品名称:	轻集料混凝土小型空心砌块

Sample Name

委托单位: 三河市明晟建筑材料有限公司

Client

Test Type









建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703DW103

第1页共2页

检验结论		455	7年03月2日检验测试章》				
	经检验,送检样品的密度等级标准 GB/T 15229-2011 中密度等级 1 标要求。	、抗压强度、放射 000 级、强度等级	性的检验结果符合 MU3.5 级的技术指				
检验项目	1. 密度等级 2. 抗压强度 3. 放射性						
检验依据	GB/T 15229-2011《轻集料混凝土小型空心砌块》						
样品数量	8 块	样品状态	块状				
来样日期	2017年03月10日	规格型号	395mm×195mm ×90mm				
生产日期	2016年11月15日	样品编号	超影響				
生产单位	三河市明晟建筑材料有限公司	等级	MU3.5				
委托单位	三河市明晟建筑材料有限公司	商标	可語				
样品名称	轻集料混凝土小型空心砌块	检验类别	委托检验				

备注:(此处空白)

批 准:

编

北京市朝阳区管庄中国建材院内北楼 检验单位地址:

电话: 010-51164723



建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703DW103

第2页 共2页

序号	检验项目	标准要求 ≥910, ≤1000		检验结果 940		单项结论
	密度等级/(kg/m³) (密度等级 1000 级)					合格
抗压强度/MPa (强度等级 MU3.5)		平均值	最小值	平均值	最小值	A 16
	≥3.5	≥2.8	3.7	3.1	合格	
放射性 (放射性比活度)	内照射指数 (I _{Ra}) ≤1.0		0.3		合格	
	外照射指数 (I _y) ≤1.0		0.4		合格	

(以下空白)

备注:(此处空白)

建筑材料工业技术监督研究中心

说 明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.
4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾

4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report. 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结

果仅对来样负责。
The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and

information is out of our responsibility.

6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.

本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com