



检验报告

TEST REPORT

中心编号(No.): 201605AC248

起的推拔营

样品名称:	聚合物抗裂砂浆		
Sample Name			
受检单位: Client	北京清添兴业建筑材料有限公司		
检验类别:	抽样检验		
Test Type	943694393394369469479		

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

150002283084

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201605AC248

第1页共2页

			24 24 24			
产品名称	聚合物抗裂砂浆	检验类别	抽样检验			
受检单位	北京清添兴业建筑材料有限公司	生产日期				
生产单位	北京清添兴业建筑材料有限公司	规格型号	于粉型			
抽样地点	企业成品库房	商标				
抽样人	陈嘉宇 谷冰莹	等级	45545			
抽样日期	2016年05月25日	抽样数量	10kg			
样品状态	粉板	抽样基数	5t 5 5 5			
抽样单位	建筑材料工业干混砂浆产品质量监督检验测试中心					
检验依据	DB11/T 584-2013《保温板薄抹灰外墙外保温施工技术规程》					
检验项目	1. 拉伸粘结强度(与模塑板) 2. 吸水量 3. 可操作时间 4. 柔韧性 5. 不透水性					
检验结论	*经检验,抽检样品的拉伸粘结强度(与模塑板)、吸水量、可操作时间、柔韧性、不透水性的检验结果符合标准 DB11/T 584-2013 中抹面胶浆的技术指标要求。*					
	こうしょ とり こうりょうしょ こうしょ	STEP AND	11/2/2			

备注: (此处空白)

批准: 6

制: お恋

检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



建筑材料工业技术监督研究中心

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201605AC248

第2页共2页

序号	检验项目		标准要求 (抹面胶浆)	检验结果	单项结论
	拉伸粘结强度 (与模塑板) /MPa	常温常态	≥0.10	0.11	合格
		浸水 48h, 干燥 2h	≥0.06	0.07	合格
		浸水 48h, 于燥 7d	/ ≥0.10	0.10	合格
		耐冻融	≥0.10	0.10	合格
2	吸水量/ (g/m²)		≤500	492	合格
3	可操作时间/h		1.5~4.0	2.0	合格
45444	秦初性	压折比	≤3.0	2.9	合格
		抗冲击性	3.7级	3.7 级	合格
5	不透水性		试样抹面层内 侧无水渗透	试样抹面层内 侧无水渗透	符合

备注:(1)拉伸粘结强度(与模塑板)、吸水量、可操作时间、不透水性试验依据标准 JGJ 144-2004 规定的试验方法进行检验;

- (2) 柔韧性 (压折比) 试验依据标准 JG 149-2003 规定的试验方法进行检验:
- (3) 柔韧性(抗冲击性) 试验依据标准JC/T993-2006 规定的试验方法进行检验;;
- (4) 配比: 粉:水=4:1;
- (5) 模塑板规格: 18kg/m³。



检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出, 逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

皇幸

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com

