



检

验

报

出口

TEST REPORT

中心编号(No.): 201705AW163

样品名称:

粉刷石膏底层

Sample Name

委托单位:

北京创美龙达科技有限公司

Client

检验类别:

委托检验

Test Type

技术

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortan







中心编号(No.): 201705AW163

150002283084国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

样品名称 於別石膏底层 检验类别 委托检验 委托单位 北京创美龙达科技有限公司 标 商 生产单位 北京创美龙达科技有限公司 级 生产日期 样品编号 来样日期 2017年05月08日 规格型号 于粉型 样品数量 20kg 样品状态 粉状 检验依据 GB/T 28627-2012《抹灰石膏》 检验项目 1、抗折强度 20 抗压强度 3. 拉伸粘结强度 *经检验,送检样品的抗拆强度、抗压强度、拉伸粘结强度的检验结

检验结论

签发日期: 2017年05月24日

(检验测试章)

第1页共2页

备注:(此处空台)

在建位员专用

批准号加入市核: 北京 编制: 书. 亮

果符合标准 GB/T 28627-2012 中底层抹灰石膏的技术指标要求。*

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201705AW163

第2页共2页

是是	检验项目	标准要求 (底层抹灰石膏)	检验结果	单项结论
	抗斯强度IMPa		2.80	
	抗压强度AMPa		\$3.90 \$3.90 \$4.50	
路	拉伸點結開度/MPa	0.4	0.42	7682 7682 7682

(以下空白)

备注:配比:粉:水=1.0:0.40。

说 明

Notice

- 1、本报告无由心"检验测试章个和骑缝章无效。 This test report is invalid without the seal.
- 21 本报告无广编制,审核、批准"八签字无效。

This test report is invalid without the signatures of the related persons.

- 3、一本报告涂改、一部分复印无效。
 - This test report is invalid if erased, altered or copied partially,
- 4、对本报告若有异议,应于收到报告之目起中五个工作目内向本中心提出,逾 期怨不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托太提供上中心不对真实性负责,一委托检验结 果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张、复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code): 100024

电话(Tel):(010)51164723-51164718

传真(Fax):(010)51164724

报告真伪查询(Tel):(010)51164716

网址(Web):http://www.dmtc.org.en/

电子邮箱(E-mail): dmtc2007@163.com



