



150002283084

TEST REPORT

中心编号(No.): 201705AW299

样品名称:

盾构注浆配套预拌砂浆

Sample Name

委托单位: 三河市福山绿洲新型建材有限公司

Client

检验类别:

委托检验

Test Type

国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







150002283084(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201705AW299

TO DOWN	100-1-50H100HM 544 101 101 1	一工人。大人以一大人	
样品名称	盾构注浆配套预拌砂浆	检验类别。秦托检验	
委托单位	三河市福山绿洲新型建林有限公司	海沿海中	
生产单位	三河市福山绿洲新型建和有限公司	等 2级 M5 20 20 20 20 20 20 20 20 20 20 20 20 20	
生产日期		样品编号	
来样日期	2017年05月24日	规格型号 100	
样品数量	20kg	样品状态。粉末	
检验依据	(B/I)25181-2010 (新洋沙楽》		
检验项目	①. / 葉结时间		
检验结论	整檢驗, 送检样品的凝结时间, 286 GB/T-25181-2010 東于混抹灰砂浆-普通报	灰砂浆 M5 的技术指标要求。*	
备注:0世级	签发日期: 3011至年 07 月 62 日 「た险验测试章)」 (文句)		

批准: [



(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201705AW299

第2页共2页

	检验项目	标准要求 (并混抹灰砂浆 普通抹灰砂浆 M5)	检验结果	单项结论
紹	影響的剛力			
	28d 抗压强度/MPa	\$3,000 P		

(以下空白)

备注:配比:粉:水=1.0:0.18。

说 明

Notice

- 1、本报告无由心"检验测试章"和骑缝章无效。
 - This test report is invalid without the seal.
- 本报告无广编制、审核、批准介签字无效。

This test report is invalid without the signatures of the related persons.

- 3、本报告涂改、部分复印无效。
 - This test report is invalid if erased, altered or copied partially.
- 生。对本报告若有异议。应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 大。本报告采用防伪纸张,复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code): 100024

电话了TelD: (0100)51164723 51164718

传真(Fax):(010),51164724

报告真伪查询(Tel):(010)。51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱(E-mail)。dmtc2007@163-com



