



检验报告

TEST REPORT

中心编号(No.): 201703AW316

样品名称:	2550年10年10年10日10日1
Sample Name	
委托单位: Client	河北普莱斯德绝热材料有限公司
检验类别: Test Type	委托检验

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





150002283084(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703AW316

第1页共2页

The state of the s		- V - V	73 1 25 71 12			
样品名称	聚苯板	检验类别	委托检验			
委托单位	河北普莱斯德绝热材料有限公司	商标	普莱斯德			
生产单位	河北普莱斯德绝热材料有限公司	等 级				
生产日期		样品编号	超级程			
来样日期	2017年03月14日	规格型号				
样品数量	840202020	样品状态	核 状			
检验依据	GB/T 10801.1-2002《絶热用模塑聚苯乙烯泡沫塑料》					
检验项目	1. 表观密度 2. 压缩强度 3. 导热系数					
检验结论	*经检验, 送检样品的表观密度、压缩强度、导热系数的检验结果符合标准 GB/T 10801.1-2002 中 II 类的技术指标要求。*					
	全国的	日期: 2017	年 03 月 23 日 验测试章)			
备注:(此处	# POLITOPITA POLITOP	1000	WIN TU TO			

备注:(此处空白)

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703AW316

第2页共2页

序号	检验项目	标准要求 (II 类)	检验结果	单项结论
i	表观密度,kg/m³	≥20.0	20.1	合格
2	压缩强度, kPa	≥100	132	合格口包
3	导热系数, W/(m⋅K)	≤0.041	0.039(平均温 度: 25,00°C)	合格

备注:(此处空白)

说。明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmte2007@163.com