



检验报告

TEST REPORT

中心编号(No.): 201703AW407

 样品名称:
 外墙柔性腻子

 Sample Name
 北京诚信欣华工贸有限公司

 委托单位:
 北京诚信欣华工贸有限公司

 Client
 委托检验


 Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业于混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

10000413





建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703AW407

第1页共2页

	2011-001111-07		1 / 2 / /			
样品名称	外墙柔性腻子	检验类别	委托检验			
委托单位	北京诚信於华工貿有限公司	商标	经进程			
生产单位	北京诚信欣华工贸有限公司	等级	的珍色			
生产日期	经的现在分别	样品编号				
来样日期	2017年03月20日	规格型号	千粉型			
样品数量	20kg	样品状态	粉状			
检验依据	JG/T 157-2009《建筑外墙用腻子》					
检验项目	1. 初期干燥抗裂性 2. 耐水性 3. 粘结强度 (标准状态)					
检验结论	*经检验,送检样品的初期干燥抗裂性、耐水性、粘结强度(标准》 态)的检验结果符合标准 JG/T 157-2009 中普通型 (P) 的技术指标要求					
	签发日期: 2017年04月05日					
经经验	(检验测试章)					

备注:(此处空白)

批准: 编制: 苏亮

电话: 010-51164723

邮编: 100024

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703AW407

第2页共2页

序号	检验项目		标准要求 [普通型(P)]	检验结果	单项结论
	初期干燥抗 裂性 (6h)	单道施工厚度 ≤1.5mm 的产品	1mm 无裂纹	1mm 无裂纹	符合
2	耐水性 (96h)		无异常	无异常	符合
3	粘结强度 /MPa	标准状态	≥0.60	0.76	合格

(以下空白)

备注: 配比: 粉: 水=1.0: 0.40。

说 明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com