

# 检验报告

TEST REPORT

中心编号(No.): 201702AC204



样品名称: 聚合物抗裂砂浆

Sample Name

受检单位: 北京振远立博科技发展有限公司

Client


检验类别:

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





## 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

#### TEST REPORT

中心编号(No.): 201702AC204

第1页共2页

产品名称	聚合物抗製砂浆	检验类别	抽样检验			
受检单位	北京振远立博科技发展有限公司	生产日期				
生产单位	北京振远立博科技发展有限公司	规格型号	干粉型			
抽样地点	企业成品库房	商标				
抽样人	陈嘉宇、谷冰莹	等级	部。路			
抽样日期	2017年02月22日	抽样数量	20kg			
样品状态	***************************************	抽样基数				
抽样单位	建筑材料工业干混砂浆产品质量监督检验测试中心					
检验依据	JG 149-2003《膨胀聚苯板薄抹灰外墙外保温系统》					
检验项目	1. 拉伸粘接强度 (与膨胀聚苯板: 原强度、耐水) 2. 柔韧性					
检验结论	*经检验, 抽检样品的拉伸粘接强度(与膨胀聚苯板:原强度、水)、柔韧性的检验结果符合标准JG 149-2003 中抹面胶浆的技术指标。*					
開始	签发日期: 2017年 03 月 24 日 (检验测试章)					

奋注:(此处至日)

批准:

之、审核: 延和

编制: 扶急

#### (国家)建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

#### TEST REPORT

中心编号(No.): 201702AC204

第2页 共2页

序号	检验项目		标准要求 (株面胶浆)	检验结果	单项结论
	拉伸粘接强度 (与膨胀聚苯板) /MPa	原强度	≥0.10, 破坏界面在膨 胀聚苯板上	0.12, 破坏界面在膨 胀聚苯板上	4000
		耐水	≥0.10, 破坏界面在膨 胀聚苯板上	0.11, 破坏界面在膨 胀聚苯板上	464
2	柔韧性 (水泥基)	抗压强度/ 抗折强度		2.9	合格

(以下空白)

备注: (1) 配比: 粉:水=4:1;

(2) 聚苯板规格: EPS 板 18kg/m3。

### 说。明

#### Notice

- 本报告无中心"检验测试章"和骑缝章无效。
   This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
  This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
   This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
  This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com