



# 检验报告

TEST REPORT

中心编号(No.): 201604BW245

样品名称: 陶瓷墙地砖胶粘剂

Sample Name

委托单位: 德國必優集團有限公司

Client

检验类别: 委托检验

Test Type

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家) 建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 报告

TEST REPORT

中心编号(No.): 201604BW245

第1页共2页

强强	签发日期: 2016年05月27日 (检验测试章)				
检验结论	*经检验,送检样品的拉伸胶粘原强度、浸水后的拉伸胶粘强度、热老化后的拉伸胶粘强度的检验结果符合标准 JC/T 547-2005 中普通型胶粘剂 C1型的技术指标要求。*				
检验项目	1. 拉伸胶粘原强度 2. 浸水后的拉伸胶粘强度 3. 热老化后的拉伸胶粘强度				
检验依据	JC/T 547-2005《陶瓷墙地砖胶粘剂》				
样品数量	20kg	样品状态	粉状		
来样日期	2016年04月25日	规格型号			
生产日期	2016年03月22日	样品编号			
生产单位	德國必優集團有限公司	等级			
委托单位	德國必優集團有限公司	商标	網路總		
样品名称	陶瓷地砖胶粘剂	检验类别	委托检验		

批 准:

编 制:

检验单位地址: 北京市朝阳区管庄中国建材院内北楼 电话: 010-51164723

邮编:

100024

#### (国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201604BW245

第2页 共2页

序号	检验项目	标准要求 (普通型胶粘剂 C1型)	检验结果	单项结论
	拉伸胶粘原强度/MPa	15.80.5 FE	13.5	合格。
122	浸水后的 拉伸胶粘强度/MPa	≥0.5	0.6	合格。
	热老化后的 拉伸胶粘强度/MPa	≥0.5	0.6	合格

(以下空白)

备注: 配比: 粉:水=1.0:0.25。

#### 说明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。
  This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
  This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
   This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

网址 (Web); http://www.dmtc.org.cn/

电子邮箱(E-mail): dmtc2007@163.com

