



验报告

REPORT TEST

中心编号(No.): 201705AW263

样品名称:

瓷砖粘结剂

Sample Name

委托单位:

唐山化德建筑材料有限公司

Client

检验类别:

委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar









(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201705AW263 第1页共2页

样品名称		检验类别	12.00 Market
委托单位	唐山征德建筑材料有限公司	商。标	
生产单位	唐山花德建筑材料有限公司	等。级	
生产目期		样品编号	
来样日期	2017年 05月 19日	规格型号	
样品数量	20kg	样品状态	
检验依据	JCA:547-2005《陶瓷墙地砖版粘剂》		
检验项目	1. 粒神胶粘原强度 2. 浸水后的拉伸胶粘强度		
	* 经检验, 送检样品的拉伸胶粘原强度、浸水后的拉伸胶粘强度的检验结果符合标准 JC/I 547-2005 申普通型胶粘剂 (C1) 的技术指标要求。		

检验结论

签发日期: 2017年06月18日 (检验测试章)

备注:(此处空台)

批准:

(And) 审核: 送和

编制:苏亮

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

验报告

TEST REPORT

中心编号(No.): 201705AW263

第2页共2页

	标准要求 【普通型胶粘剂 (C1)】	检验结果	单项结论
持律胶粘原强度/MPa	# 30.5	0.8	
浸水后的拉伸胶粘强度 /MPa	0.5		

备注: 配比: 粉:水-4:1。

说 明

Notice

本报告无中心"检验测试章"和骑锋重无效。

This test report is invalid without the seal.

本报告无广编制、审核、批准广签字无效

This test report is invalid without the signatures of the related persons.

3〇本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially

- 4、对本报告若有异议,应证收到报告之日起于五个工作印肉 向本中心提出。通 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、一委託检验样品和委托信息由委托入提供,中心不对真实性负责,委托检验结 果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告的法律责任由建筑材料工业技术监督研究中心承担

The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.

7二本报告采用防伤纸张,复印后应带有网络底纹。

This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address),工北京市朝阳区管庄东里一号北楼

No. I Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code): 100024

电话(Teld)(010)与1164723与H64718

传真(Fax):(010)51164724

报告其伪查询(Tel):(1010),51164716

Web): http://www.dmtc.org.cn/

电子邮箱(E-mail):dmtc2007@163.com

