



检验报告

TEST REPORT

中心编号(No.): 201707DW002



样品名称:	砌块粘结剂
Sample Name	
委托 <mark>单位:</mark> Client	北京六合财建筑材料有限公司
检验类别: Test Type	委托检验

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry, Center for Quality Supervision and Test of Dry-mixed Mortar







150002283084 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201707DV	W002
---------------------	------

第1页 共2页

1 6 2 1 5 (1 to.). 201707DW002		第10 共20		
样品名称	砌块粘结剂	检验类别	委托检验	
委托单位	北京六合财建筑材料有限公司	商标		
生产单位	北京六合财建筑材料有限公司	等 级	M10	
生产日期	2017年07月20日	样品编号	REPERT	
来样日期	2017年07月24日	规格型号		
样品数量	20kg	样品状态	粉状	
检验依据	GB/T 25181-2010《预拌砂浆》			
检验项目	1. 保水率 2. 凝结时间	3.28d 抗压强度		
检验结论	*经检验,送检样品的保水率、符合标准 GB/T 25181-2010 中干混硫标要求。*	·筑砂浆-普通砌筑 签发日期:	砂浆M10的技术指 17年08月31日	
			(检验测试章)	
备注:(此处	委 自)于了一个工作与工作	12052	建設時報ノーニ	

批 准:

检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723



建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201707DW002

第2页共2页

序号	检验项目	标准要求 (干混砌筑砂浆-普 通砌筑砂浆 M10)	检验结果	单项结论
	保水率/%	25 ≥88	98.7	合格
2	凝结时间/h	3~9	5.5	合格
3	28d 抗压强度/MPa	≥10.0	14.6	合格

(以下空白)

电话: 010-51164723

邮编: 100024

备注: 配比: 粉:水=1,0:0.21。

说 明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>dmtc2007@163.com</u>





