



# 检验报告

TEST REPORT

中心编号(No.): 201203AW134


可对用气

样品名称:	抹灰砂浆		
Sample Name			
委托单位: Client	北京德科振邦科技发展有限公司		
检验类别: Test Type	委托检验		

国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





2009003084M 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-Mixed Mortan

# 检验报告

TEST REPORT

中心编号(No.): 201203AW134

第1页共2页

中心编号(No.): <u>201203AW134</u>		第1页 共4页		
样品名称	妹灰砂浆	检验类别	委托检验	
委托单位	北京德科振邦科技发展有限公司	商标		
生产单位	北京德科振邦科技发展有限公司	样品状态	粉状	
生产日期	是自己的自己的	生产批号		
来样日期	2012年03月20日	样品编号		
样品数量	20kg	规格型号	千粉型	
检验依据	JG/T 230-2007《预拌砂浆》			
检验项目	<ol> <li>强度等级 2, 保水性 3,14d 拉伸粘结强度</li> </ol>			
检验结论	*经检验,送检样品的强度等级、保水性、14d 拉伸粘结强度的检验结果符合标准 JG/T 230-2007 中 M15 干混抹灰砂浆的技术指标要求。* 签发日期: 2012 年 06 月 28 日			

备注: (此处空白)

批准: ym

审核: 王奘从

编制:



检验学位地址:北京市朝阳区管庄中国建材院北楼

电话: 010-51164723

邮编: 100024



### (国家) 建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201203AW134

第2页共2页

序号	检验项目	标准要求	检验结果	单项结论
	<b>温度等级</b>	M15	15.6MPa	合格
2	保水性%	>88	88	合格
3	14d 拉伸粘结强度 / MPa	>0.20	0.70	合格

(以下空白)

各注:配比:粉:水=1;0.18.



### 说明

#### Notice

- 本报告无中心"检验测试章"和骑缝章无效。
   This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
- This test report is invalid if crased, altered or copied partially.

  4、对本报告若有异议。应于收到报告之日起十五日内向本中心提出。逾期怨不
- - Any doubt should inform us within 15 days after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 本报告采用防伪纸张、复印后应带有网络底纹。
   This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管止东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164723 51164718

國地 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>si13146197542@126.com</u>

