



检验报告

TEST REPORT

中心编号(No.): 201711DW109

PP 179 189	43 44 44 644 644 644 644 644 644 644 644
样品名称:	尼龙锚栓
Sample Name	
委托单位:	日照广耐橡塑有限公司
Client	
金验类别 :	委托检验
est Type	147495749574175997499749

建筑材料工业技术监督研究中心

建筑材料工业于混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







150002283084 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

1 U - m J (11U.). 2U1/1111/W 1U9	中心编号	(No.)	: 20	1711	DW1	09
----------------------------------	------	-------	------	------	-----	----

下心细与(1	(0.): 201/11DW109	第1	页 共 2 页
样品名称	尼龙锚栓	检验类别	委托检验
委托单位	日照广耐橡塑有限公司	商标	THE REAL PROPERTY.
生产单位	日照广耐橡塑有限公司	等级	超記記
生产日期		样品编号	GN001
来样日期	2017年11月15日	规格型号	Ф8mm×130mm
样品数量	20套	样品状态	打 状
检验依据	JG/T 366-2012《外墙保温用锚栓》		
检验项目	1. 圆盘抗拔力标准值		
检验结论	*依据标准 JG/T 366-2012 规定的设盘抗拔力标准值的检验结果见第 2 页。	、验方法进行检 *	验,送检样品的
	签发日	The same	E11月17日 金测试章)
备注:(此处空白)		Control of the second	教士

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201711DW109

第2页 共2页

序号	检验项目	标准要求	检验结果	单项结论
1.	圆盘抗拔力标准值, kN		0.90	是真是

(以下空白)

INITE

备注:(此处空白)

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



