



检验报告

TEST REPORT

中心编号(No.): 201606AW153

 样品名称:
 大理石瓷砖粘接剂

 Sample Name
 北京兴德昌碌商贸有限公司

 Client
 委托检验

 Test Type
 委托检验

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

150002283084

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201606AW153

第1页共2页

			~ ~ ~ ~ ~ ~		
样品名称	大理石瓷砖粘接剂	检验类别	委托检验		
委托单位	北京兴德昌碌商贸有限公司	商。标	有程皂		
生产单位	北京市昌平区兴寿鑫兴滑石粉厂	等级			
生产日期		样品编号	1874		
来样日期	2016年06月13日	规格型号	千粉型		
样品数量	20kg	样品状态	粉状子		
检验依据	JC/T 547-2005《陶瓷墙地砖胶粘剂》				
检验项目	1. 拉伸胶粘原强度 2. 浸水后的拉伸胶粘强度				
检验结论	*经检验,送检样品的拉伸胶粘原强度、浸水后的拉伸胶粘强度的机验结果符合标准 JC/T 547-2005 中普通型胶粘剂 (CI) 的技术指标要求。				
認能	签发日期: 2016年 07 月 13 日				
		【检验测	试章】		
备注:(此处空白)		一个一个一个一个	○ 【		

批准:

制: 书. 急

检验单位地址,北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201606AW153

第2页共2页

序号	检验项目	标准要求 [普通型胶粘剂 (C1)]	检验结果	单项结论
	拉伸胶粘原强度/MPa	≥0.5	0.8	合格
2	浸水后的拉伸胶粘强度 /MPa	≥0.5	0.5	合格

《以下空自》

备注: 配比: 粉:水=4:1。

邮编: 100024

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话(Tel):(010)51164723 51164718

传真(Fax):(010)51164724

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail); dmtc2007@163.com

