



# 检验 报告

#### TEST REPORT


中心编号(No.): 201710AW157

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







## 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201710AW157

第1页共2页

			NO 1 24 24 24					
样品名称	盲道砖	检验类别	委托检验					
委托单位	三河市强伟建材有限公司	商标						
生产单位	三河市强伟建材有限公司	等 级	Cc40					
生产日期		样品编号						
来样日期	2017年10月25日	规格型号	250 mm×250 mm×60m					
样品数量	50 块	样品状态	块状					
检验依据	GB 28635-2012《混凝土路面砖》							
检验项目	1. 外观质量 2. 抗压强度							
TO THE	*经检验,送检样品的外		果符合标准 GB 28635-20 作 GB 28635-2012 中抗压					



### (国家)建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201710AW157

第2页 #2页

序号		检验项目标准要求		检验结果		单项结论	
1		铺装面粘皮或缺损的 最大投影尺寸/mm	≤5		无粘皮及缺损		符合
		铺装面缺棱或掉角的 最大投影尺寸/mm	≤5		无缺棱及掉角		符合
	外观质量	铺装面裂纹	不允许		无裂纹		符合
		色差、杂色	不明显		不明显		符合
		平整度/mm	≤2.0		2.0		合格
		垂直度/mm	≤2.0		1.1		合格
2	抗压强度/MPa (抗压强度等级 Cc40)		平均值	单块 最小值	平均值	单块 最小值	合格
			≥40.0	≥35.0	48.2	45.8	

(以下空白)

备注:(此处空白)

建筑材料工业技术监督研究中心

#### 说 明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
   This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伤纸张,复印后应带有网络底纹。
   This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



