





检验报告

TEST REPORT

中心编号(No.): 201304AW128

样品名称:	水泥大方砖				
Sample Name					
委托单位:	北京市兰芳水泥制品厂				
检验类别:	委托检验				
Test Type					

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201304AW128

第1页共2页

NO.): 201304AW128	男 Ⅰ 贝 共 ℤ 贝					
水泥大方砖	检验类别	委托检验				
北京市兰芳水泥制品厂	商标					
北京市兰芳水泥制品厂	等级					
	样品编号	THE PROPERTY.				
2013年04月03日	规格型号	(495×495×95)mm				
1组	样品状态	块状, 外观完好				
JC/T 446-2000《混凝土路面砖》						
1. 抗压强度						
JC/T 446-2000 中抗压强度等级	Cc30 的技术指标要求 签发日期: 2013年	●				
	水泥大方砖 北京市兰芳水泥制品厂 北京市兰芳水泥制品厂 2013年04月03日 1组 JC/T 446-2000《混凝土路面砖》 1. 抗压强度 * 经检验, 送检样品。 JC/T 446-2000 中抗压强度等级	水泥大方砖 检验类别 北京市兰芳水泥制品厂				

备注: (此处空白)

批准: (

审核: 王安如

编制:



检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201304AW128

第2页共2页

序号	检验项目	标准要求 (抗压强度等级 Cc30)		检验结果		单项结论
1 抗压强度, N	抗压强度, MPa	平均值	单块 最小值	平均值	单块 最小值	合格
	≥ 30.0	≥ 25.0	33.4	32.5		

备注: (此处空白)

说明

Notice

- 本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期恕不 受理。
 - Any doubt should inform us within 15 days after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164723 51164718

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): sj13146197542@126.com

