



检验报告

TEST REPORT

中心编号(No.): 201703AW142




样品名称: Sample Name	蒸压加气混凝土砌块
委托单位: Client	三河市华奥新型墙体材料有限公司
检验类别:	*************************************

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Content for Quality Supervision and Test of Dry-mixed Mortar





建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703AW142

第1页共2页

	1017. 2011001111112		ALK MAK					
样品名称	蒸压加气混凝土砌块	检验类别	委托检验					
委托单位	三河市华奥新型墙体材料有限公司	商标	TAPETE TO MA					
生产单位	三河市华奥新型墙体材料有限公司	等级	B06 A5.0					
生产日期	Partition of the state of the s	样品编号						
来样日期	2017年03月03日	规格型号	B06 A5.0					
样品数量	64 块	样品状态	块块					
检验依据	GB 11968-2006《蒸压加气混凝土砌块》							
检验项目	1. 千密度 2. 立方体抗压强度	3. 导热系数	4. 抗冻性					
检验结论	*经检验,送检样品的干密度、。 准 GB 11968-2006 中 B06 级-优等品的 检验结果符合标准 GB 11968-2006 中 签发目	的技术指标要求 A5.0 级的技术 日期: 201天年	; 立方体抗压强度的					
备注:(此处	POLENT TOTAL	プロイエウム 「高部の対策を行っている」 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、「大きい。 では、 では、 では、 では、 では、 では、 では、 では、						
田江:「此义	はおっていれていることのよう		工作学工作工					

制、书意



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortan

检验报告

TEST REPORT

中心编号(No.): 201703AW142

第2页共2页

7 100				10112000				
序号	检验项目		标准要求 (B06级-优等品)		检验结果		单项 结论	
Pip	干密加	干密度/ (kg/m³)		干密度/ (kg/m³) ≤600		590		合格
2	立方体抗压强度/MPa		平均值	单组 最小值	平均值	单组 最小值	合格	
44	123	15.0 级)	≥5.0	≥4.0	5.2	4.9		
3	导热系数(干热)/[W/(m·k)]			0.16	0.15(平 25.00	The second secon	合格	
4	抗冻性	质量损失率/%	€5.0		3.6		122	
强	融循环)	(15次冻 融循环) 冻后强度/MPa	\$32\$	4.0	2224	结组	合格	
17-3	TOTAL VICE I	THE STATE OF THE S				The state of the	100	

(以下空白)

电话: 010-51164723

邮编: 100024

备注:(此处空白)

说。明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com