



TEST REPORT

中心编号(No.): 201603CW022G1

样品名称:

乐涂仕硅藻土

Sample Name

委托单位: 吉林省德润建筑功能材料有限公司

Client

检验类别:

委托检验

Test Type

建筑材料工业技术监督研究中心 Technical Supervision and Research Center of the Building Materials Industry



建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

检验报告

TEST REPORT

中心编号(No.): 201603CW022G1

第1页共2页

	The state of the s	20 1 20 1 2 20		
乐涂仕硅藻土	检验类别	委托检验		
吉林省德润建筑功能材料有限公司	商标	乐涂仕		
吉林省德润建筑功能材料有限公司	等级	超级		
	样品编号	起電		
2016年03月31日	规格型号			
6kg	样品状态	粉状。		
JC/T 2177-2013《硅藻泥装饰壁材》				
1. 甲醛净化性能 2. 2. 2. 2. 2. 2. 2. 2. 2. 2. 2. 2. 2.				
经检验,送检样品的甲醛净化 2177-2013 的技术指标要求。		果符合标准 JC/T		
签发日期: 2016 年 06 月 08 日				
	吉林省德润建筑功能材料有限公司 吉林省德润建筑功能材料有限公司 2016年03月31日 6kg JC/T2177-2013《硅藻泥装饰壁材》 1. 甲醛净化性能 *经检验,送检样品的甲醛净化 2177-2013的技术指标要求。*	吉林省德鴻建筑功能材料有限公司 商 标		

备注: (此处空白)

如 取 麻 蕨 英 批

制:

检验单位地址:北京市朝阳区管庄中国建材院内北楼 电话: 010-51164723



建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

检验报告

TEST REPORT

中心编号(No.): 201603CW022G1

第2页共2页

		THE THE PROPERTY OF THE PROPER		
亞	样品类型	胡锦鞋	路路路	群群
样品	品涂刷量 (样品量)	3kg/m²		
語	开灯时间	12 12 12 148h		
盤	试验条件	温度(20±2) C, 相对湿度(50±10)%		
序号	检验项目	标准要求	检验结果	单项结论
	甲醛净化性能(%)	≥80	83.0	合格。

(以下空白)

备注: (此处空白)

说明

Notice

1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.

2、本报告无"编制、审核、批准"签字无效。

This test report is invalid without the signatures of the related persons.

3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期恕不受理。

Any doubt should inform us within 15 days after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
The legal responsibility of this test report is charged with Technical Supervision and Research Center of Building Materials Industry.

7、本报告采用防伪纸张,复印后应带有网络底纹。

This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com