



检验报告

TEST REPORT

中心编号(No.): 201707DW005

THYTT

样品名称:	JS 复合防水涂料
Sample Name	
委托单位: Client	北京联和象尚化工科技有限公司
检验类别:	委托检验
Test Type	

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







150002283084 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201707DW005

第1页共2页

样品名称	JS 复合防水涂料	检验类别	委托检验				
委托单位	北京联和象尚化工科技有限公司	商标	冠润德				
生产单位	北京冠润德防水科技有限公司	等级					
生产日期		样品编号					
来样日期	2017年07月26日	规格型号	I型				
样品数量	粉料 2kg,液料 2kg	样品状态	粉状,液态				
检验依据	GB/T 23445-2009《聚合物水泥防水涂料》						
检验项目	 1. 固体含量 2. 拉伸强度(无处理) 3. 断裂延伸率(无处理) 4. 低温柔性 5. 不透水性 						
检验结论	*经检验,送检样品的固体含量、 (无处理)、低温柔性、不透水性的检 中 I 型的技术指标要求。*						

备注:(此处空白)

制:

检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201707DW005

第2页共2页

序号	检验项目 固体含量/%		标准要求 (I型)	检验结果	单项结论
1			≥70	74	合格
2	拉伸强度	无处理/MPa	≥1.2	1.3	合格
3	断裂伸长率	无处理/%	,	208	合格
4	低温柔性 (Φ10mm 棒)		-10°C无裂纹	-10°C无裂纹	合格
5	不透水性(0.3MPa, 30min)		不透水	不透水	符合

(以下空白)

备注: 配比: 粉:液=1.0:1.0。

说 明

Notice

- 本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.

本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真(Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



