

150002283084

TEST REPORT

中心编号(No.): 201701AW035

样品名称:

瓷砖粘结剂

Sample Name

委托单位:

北京通达利建筑材料厂

Client

检验类别:

委托检验

Test Type

(国家)建筑材料(业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry mixed Mortar





150002283084(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

TEST REPORT

中心编号(No.): 201701AW035

170	10.4.7.501) 01.2.1.003 OH TUT	THOTE	火大大人	
样品名称		检验类别	15.50 ASSESSED TO SEED	
委托单位	北京通达利建筑林耕州	爾品標		
生产单位	北京通达利建筑材料工	等级		
生产日期		样品编号		
来样日期	2017年01月20日	规格型号		
样品数量		样品状态		
检验依据	JC/T/547-2005《陶瓷墙地砖胶料剂》			
检验项目	1. 拉伸胶粘原强度 2. 浸水后的超伸胶粘强度			
检验结论	*经检验,送检样品的拉伸胺黏原强,验结果符合标准JC/T 547-2005 中普通型*	胶粘剂(C1)	的技术指标要求。	
备注:(此处				

批准:



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201701AW035

第2页共2页

		标准要求 【普通型胶料剂 (Ci)】	检验结果	单项结论
語	指種酸點原强度MPa	0.5	0.8	
	浸水后的拉伸胶粘强度 MPa	0.5	2505 2505 2505 2505 2505 2505 2505 2505	

备注,配比,粉:水=4:1。

说 Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议。应于收到报告之日起中五个工作自内向本中心提出。逾 期怨不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 51 委託检验样品和委托信息,由委托太提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7. 本报告采用防伤纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code): 100024

电话(Tel):(010);51164723·51164718

传真(Fax):(010) 51164724

报告真伪查询(Tel):(010) 51164716

Mil (Web); http://www.dmte.org.en/

电子邮箱(E-mail):dmtc2007@163.com