



检验报告

TEST REPORT

中心编号(No.): 201608DW004G1



样品名称:	灰砂砖
Sample Name	
委托单位: Client	三河市筑城兴盛新型建材厂
检验类别:	委托检验
Test Type	

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Conter for Quality Supervision and Test of Dry-mixed Mortar







建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201608DW004G1

第1页共2页

		カー火六乙火
灰砂砖	检验类别	委托检验
三河市筑城兴盛新型建材厂	商标	
三河市筑城鑫鼎工贸有限公司	等 级	MU10
2016年08月04日	样品编号	
2016年08月04日	规格型号	225mm×105mm ×45mm
10 块	样品状态	块状
GB 11945-1999《蒸压灰砂砖》	P. B. F. S.	FIFTH
1. 强度级别(抗压强度)		
经检验,送检样品的强度级别11945-1999 中强度级别 MU10 的技	术指标要求。	结果符合标准 GE 6 年 08 月 30 日
		签发日期: 201

备注:本报告是对 201608DW004 的更改,本报告发出之日起,原报告作品

批 准: (



检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201608DW004G1

第2页 共2页

序号	检验项目		标准要求		检验结果		单项结论
	强度级	抗压强	平均值	单块值	平均值	单块值	A 10
200	别 MU10	度,MPa ≥1	≥10.0	≥8.0	13.6	12.2	合格

(以下空白)

1	1	1		
ALT VA				COT
THEFT	101	1-01	12/14	7130
		100		and the second

备注: (此处空白)

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com