




检验报告

TEST REPORT

中心编号(No.): 201611DW132



样品名称:	灰砂砖
Sample Name	
委托单位: Client	三河市崇源新型建材有限公司
检验类别: Test Type	委托检验

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201611DW132

第1页共2页

备注:(此久		THE PARTY NAMED IN	16年11月30日 (检验测试章)				
检验结论	*经检验,送检样品的强度级别中强度级别 MU10 的技术指标要求		标准 GB 11945-199				
检验项目	1. 强度级别						
检验依据	GB 11945-1999《蒸压灰砂砖》						
样品数量	10块 10块 100 100 100 100 100 100 100 100	样品状态	块状				
来样日期	2016年11月21日	规格型号	225mm×105mm ×44mm				
生产日期	2016年10月01日	样品编号	は記録				
生产单位	三河市崇源新型建材有限公司	等级	MU10				
委托单位	三河市崇源新型建材有限公司	商标	話記句				
样品名称	灰砂砖	检验类别	委托检验				

批 准:

术监督研究中心

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201611DW132

第2页共2页

邮编: 100024

电话: 010-51164723

序号	检验项目		检验项目标准要求		检验结果		单项结论
	報	抗压强度,	平均值	单块值	平均值	单块值	合格
强度	MPa	≥10.0	≥8.0	14.8	13.9	超级	
	1 级别 MU10		平均值	单块值	平均值	单块值	4 4 4 7 7 7 7 8 9 8 9 7 7 7 8 8 8 8 8 8 8 8 8
			≥2.5	≥2.0	3.2	2.9	

(以下空白)

备注:(此处空白)

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>dmtc2007@163.com</u>

