



# 检验报告

TEST REPORT

中心编号(No.): 201712BW171



样品名称: 外墙耐水腻子

Sample Name

委托单位: 大连志恒众鑫建筑工程材料有限公司

Client

检验类别:

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201712BW171

第1页 共2页

样品名称	外墙耐水腻子	检验类别	委托检验	
委托单位	大连志恒众鑫建筑工程材料有限公司	商标		
生产单位	大连志恒众鑫建筑工程材料有限公司	等级	語語等	
生产日期		样品编号		
来样日期	2017年12月29日	规格型号		
样品数量	10kg	样品状态	**************************************	
检验依据	JG/T 157-2009《建筑外墙用腻子》			
检验项目	1. 施工性 2. 打磨性 4. 耐碱性 5. 耐水性	3. 吸水量 6. 粘结强度	(标准状态)	
检验结论	*经检验,送检样品的施工性、打 粘结强度(标准状态)的检验结果符合 的技术指标要求。*	JTATH		

检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



#### (国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201712BW171

第2页共2页

序号	检验项目	标准要求 柔性(R)	检验结果	单项结论
超	<b>海王性</b>	刮涂无障碍	刮涂无障碍	持命是
22		手工可打磨	手工可力磨	
132	吸水量(g/10min)	€2.0	34336	合格
	耐碱性 (48h)	/ 无异常	<b>无异常</b>	符合
55	耐水性 (96h)	<b>元异常</b>	元异常	符合工
6	粘结强度 /MPa	≥0.60	0.78	合格

(以下空白)

备注:配比:粉:水=1.0:0.30。

### 说明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。
  This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
   This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
  This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmte2007@163.com

