



检验报告

TEST REPORT

中心编号(No.): 201712DW102



样品名称: 水泥发泡剂

Sample Name

委托单位: 武汉金牌建设有限公司

Client

检验类别:

Test Type

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201712DW10	02
-----------------------	----

第1页共2页

检验结论			7年12月15日 检验测试章)		
	*经检验,送检样品的发泡信符合标准 JC/T 2199-2013 中泡沫/		The second secon		
检验项目	1. 发泡倍数 2. 1h 沉降距 3. 1h 泌水率				
检验依据	JC/T 2199-2013《泡沫混凝土用泡沫剂》				
样品数量	Skg	样品状态	液态 22.52		
来样日期	2017年12月05日	规格型号	经经验		
生产日期		样品编号			
生产单位	武汉金牌建设有限公司	等级	超超到		
委托单位	武汉金牌建设有限公司	商标	JINP		
样品名称	水泥发泡剂	检验类别	委托检验		

批准:

编



检验单位地址;北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201712DW102

第2页共2页

序号	检验项目	标准要求 (含格品)	检验结果	单项结论
	发泡倍数	15~30		合格
2	Ih 沉隆距/mm	\$70 \$70		合格
33	1h 泌水率/%	≤ 80	78	合格

(以下空白)

备注:水泥发泡剂稀释比例:泡沫剂:水=1:30。

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



