



# 检验报告

TEST REPORT

中心编号(No.): 201707AW151



样品名称: A型干拌复合轻集料混凝土 Sample Name

委托单位: 北京亿程宏达建筑装饰有限公司

Client

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





150002283084(国家)建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201707AW151

第1页共2页

生产单位生产日期	北京亿程宏达建筑装饰有限公司	等 级 样品编号				
来样日期	2017年07月14日	规格型号	認認			
样品数量	100kg	样品状态	颗粒与干粉料的混合物			
检验依据	JGJ 51-2002《轻骨料混凝土技术规程》 12BJ1-1《工程做法》					
检验项目	1. 干密度 2. 抗压强度 3. 导热系数					
THUT	*依据标准 JGJ 51-2002 规定的试验方法进行检验,送检样品的干密度、抗压强度、导热系数的检验结果达到 12BJ1-1 中干拌复合轻集料混凝土垫层 A型 (用于屋面找坡层或抗压强度要求≤1.0MPa 的楼面)的技术指标要求。*  签发日期: 2017 年 08 月 19 日 (检验测试章)					

备注:(此处空白)

制: 书亭

#### (国家)建筑材料工业技术监督研究中心

# 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201707AW151

第2页共2页

序号	检验项目	标准要求 [干拌复合轻集料混凝 土垫层 A 型(用于屋面 找坡层或抗压强度要求 ≪1.0MPa 的楼面)]	检验结果	单项 结论
	千密度/ (kg/m³)	≤600	482	合格
2	抗压强度/MPa	≥15	1.6	合格
253	导热系数/[ W/(m⋅K)]	<b>₹0.1</b>	-0.1(平均温度: 25.00°C)	合格

(以下空白)

备注: 配比: 料: 水=1.0: 0.85。

检验单位地址: 北京市朝阳区管庄中国建材院内北楼 电话: 010-51164723

#### 说明

### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
   This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
   This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com

