



# 检验 报告

TEST REPORT

中心编号(No.): 201707CW134

样品名称:	海星系列	(硅藻泥

Sample Name

委托单位: 广州绿素新材料科技有限公司

Client

检验类别: 委托检验

Test Type

建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry





### 建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

# 检验报告

REPORT

中心编号(No.): 201707CW134

第1页共2页

20 Clark A Chi. Charles Co. Charles Chi. Chi. Chi.		第1页 六 4 页		
海星系列 (硅藻泥)	检验类别	委托检验		
广州绿素新材料科技有限公司	商标	有涂		
广州绿素新材料科技有限公司	等 级			
	样品编号	YT-1702		
2017年07月17日	规格型号	海星系列 YT-SF0		
2kg	样品状态	粉状		
JC/T 2177-2013 (2017)《硅藻泥装饰壁材》				
1. 甲醛净化性能				
2177-2013 (2017) 的技术指标要	求。* 日期: 2019年	i.术监察		
	海星系列(硅藻泥)  广州绿素新材料科技有限公司  广州绿素新材料科技有限公司  2017年07月17日  2kg  JC/T 2177-2013 (2017)《硅藻泥浆  1. 甲醛净化性能  *经检验,送检样品的甲醛 2177-2013 (2017)的技术指标要	广州绿素新材料科技有限公司		

备注: 生产批号: 98118051707100001。





#### 建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

## 检验报告

TEST REPORT

中心编号(No.): 201707CW134

第2页共2页

序号	检验项目	标准要求	检验结果	单项结论
1	甲醛净化性能(%)	≥80	87.1	合格

(以下空白)

备注: (1) 配比: 粉:水=1:1;

(2)涂刷量: 1kg/m2;

(3) 样品测试期间,不开启日光灯。

检验单位地址: 北京市朝阳区管庄中国建材院内北楼 电话: 010-51164723

邮编: 100024





#### 说 明

#### **Notice**

1、本报告无中心"检验测试章"和骑缝章无效。

This test report is invalid without the seal.

2、本报告无"编制、审核、批准"签字无效。

This test report is invalid without the signatures of the related persons.

3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告的法律责任由建筑材料工业技术监督研究中心承担。

The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.

7、本报告采用防伪纸张,复印后应带有网络底纹。

This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



