



验报

TEST REPORT

中心编号(No.)。201706DW111

样品名称: 玻化微珠保温砂浆

Sample Name

委托单位: 北京翔羽世纪商贸有限公司

Client

检验类别: 委托检验

Test Type

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar









建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201706DW111

第1页共2页

样品名称	被化微珠保温砂浆	检验类别	麦托检验		
委托单位	北京朔羽世纪商贸有限公司	商标			
生产单位	北京翔羽世纪商贸有限公司	等级			
生产目期	2017年06月12日	样品编号			
来样日期	2017年06月12日	规格型号			
样品数量	10kg 25 25 25 25 25 25 25 25 25 25 25 25 25	样品状态	颗粒与于粉料的混合物		
检验依据	GB/T 20473-2006《建筑保温砂浆》				
检验项目	1. 于密度 2. 抗压强度 3. 导热系数 4. 燃烧胜能级别				
检验结论	*经验验,选检样品的干密度、抗压的检验结果符合标准 GB/T 20473-2006要求。*	中建筑保温的			

批准:

编 制:



建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201706DW111

第2页共2页

	松岭项目	标准要求	检验结果	单项结论
	于密度/(kg/m³)	301-2400	365	
	抗压强度/MPa	\$2.40°54		
	导热系数(<u>干态)</u> /[W/(m-K)]	€01085	0,084 (平均温度:25.00°C)	
路	燃烧性能级别		A(A)	

(以下空白)

备注: 配比: 料:水=1.0:0.85。

说 明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、 本报告无"编制、审核、批准"签字无效。 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告来用防伪纸张,复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address)。北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code): 100024

电话(Tel)。(010)51164723 51164718

传真(Fax):(010)51164724

报告真伪查询(Tel):(010) 51164716

网址(Web):http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com

