



验报告

TEST REPORT

中心编号(No.): 201701AW037

样品名称:

聚合物抗裂砂浆

Sample Name

委托单位:

北京通达利建筑材料厂

Client

检验类别:

委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



(国家)建筑材料工业技术监督研究中心

150002283084

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201701AW037

	THE TAIR A CH	1	2417		
样品名称	聚合物就要的浆土工工工工工工工工工工工工工工工工工工工工工工工工工工工工工工工工工工工工	检验类别	* R 检验		
委托单位	北京通达利建筑林梨石	商品标			
生产单位	北京通达利建筑林梨工	等。级			
生产日期		样品编号			
来样日期	2017年01月20日	规格型号			
样品数量		样品状态			
检验依据	JG149-2003《膨胀聚苯板薄抹灰外墙外保温系统》				
检验项目	① 拉伸粘接强度(与膨胀聚苯板:原强度、耐水) 2、柔韧性				
检验结论	*经检验,送检样品的拒伸粘接强度(与膨胀聚苯板:原强度、耐水)。 柔韧性的检验结果符合标准JG149-2003 申抹面胶浆的技术指标要求。*				
备注。(此处	签发日期: 2017年 03 月 02 日 《检验测试章》				

批准: 9



检验单位地址:北京市朝阳区管压中国建材院内北楼一

电话: 010-51164723

邮编: 100024



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201701AW037

景	检验项目		标准要求 (抹面胶浆)	检验结果	单项结论
	拉伸粘接强度		≥0.10, 破坏界面在膨 胀聚苯板出	0.42, 破坏界而在膨 胀聚苯板上	
	(与膨胀聚苯 板)/MPa		≥0.10, 破坏界面在膨 胀聚苯板上	0.11、 破坏界面在膨 胀聚苯板上	
路路	(水泥基)	抗压强度/ 抗折强度	3.0	2.9	

(以下空白)

备注:(1)配比:粉:水=4:1:

(2) 聚苯板规格: EPS 板 18kg/m3。

说 Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal
- 2、本报告无"编制、审核、批准"签字无效。 This test report is invalid without the signatures of the related persons.
- 3. 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议。应于收到报告之日起七五个工作日内向本中心提出,逾
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 57 委托检验样品和委托信息由委托大提供,中心不对真实性负责,委托检验结

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伤纸张、复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code):100024

电话(Tel): (010) 51164723 51164718

传真(Fax)。(010)51164724

报告真伪查询(Tel):(010) 51164716

Mile (Web): http://www.dmtc.org.en/

电子邮箱(E-mail): dmtc2007@163.com