



# 检验报告

TEST REPORT

中心编号(No.): 201712DW002

THE RALE

Sample Name

委托单位: 香河明远新型环保建材有限公司

Client

Test Type

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







#### 建筑材料工业技术监督研究中心

#### 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201712DW002

30	(0.): <u>201712DW002</u>	第1	第1页共2页		
品名称	砌筑砂浆 DM M15	检验类别	委托检验		
托单位	香河明远新型环保建材有限公司	商标	香塔		
产单位	香河明远新型环保建材有限公司	等级	1999年		
产日期	2017年11月25日	样品编号	078		
样日期	2017年12月01日	规格型号	DM M15		
品数量	20kg	样品状态	粉状		
验依据	GB/T 25181-2010《预拌砂浆》	記記記	137125		
验项目	1. 保水率 2. 凝结时间 3. 2h 稠度损失率 4. 28d 抗压强度				
验结论	*经检验,送检样品的保水率、凝绝强度的检验结果符合标准 GB/T 25181-2 % M15 的技术指标要求。*	2010 中干混砌筑矿	失率、28d 抗压少浆-普通砌筑砂		
E。(此处空	POSTER PO		11		

批准:

检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



### 建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201712DW002

第2页 共2页

CHAI	TO TAKE	第2贝共2页		
序号	检验项目	标准要求 (干混砌筑砂浆-普 通砌筑砂浆 M15)	检验结果	单项结论
强	保水率/%	≥88	95.6	合格
2	凝结时间/h	39234	6.8	合格
3	2h 稠度损失率/%	<b>≤30</b>	22.1	合格
4	28d 抗压强度/MPa	≥15.0	17.2	合格

(以下空白)

备注: 配比: 粉:水=1.0:0.18。

#### 说 明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话(Tel): (010) 51164723 51164718

传真(Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网加 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



