





# 检验报告

TEST REPORT

中心编号(No.): 201303AW243

样品名称:	地坪砂浆
Sample Name	
委托单位: Client	北京绿宝家和科技发展有限公司
检验类别:	委托检验
Test Type	

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

2012) 建材质监认学(24号)

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201303AW243

第1页共2页

1 6 5 (1 to.). 201303 A W 243		第1页 共2页			
样品名称	地坪砂浆	检验类别	委托检验		
委托单位	北京绿宝家和科技发展有限公司	商标			
生产单位	北京绿宝家和科技发展有限公司	等级	M15		
生产日期	2013年02月	样品编号	和组织		
来样日期	2013年03月24日	规格型号	M15		
样品数量	20kg	样品状态	粉状,无结块		
检验依据	JG/T 230-2007《预拌砂浆》				
检验项目	1. 强度等级 2. 保水性 3. 凝结时间				
检验结论	*经检验,送检样品的强度等级标准 JG/T 230-2007 中 M15 干混地的签发	面砂浆的技术指挥 日期: 2013 年	标要求。* ***********************************		

备注: (此处空白)

批准:

审核: 文英州

编制:



检验单析报

선地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



#### (国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201303AW243

第2页 共2页

序号	检验项目	标准要求 (M15千混地面砂浆)	检验结果	单项结论
總	强度等级/MPa	M15	16	合格
2	保水性/%	>88	90	合格
33	凝结时间/h	3~8	4.25	合格

备注: 配比: 粉:水=1:0.13。

#### 说 明 Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"批准、审核、编制"签字无效。
  This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
  This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期恕不 受理。
  - Any doubt should inform us within 15 days after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 本报告采用防伪纸张,复印后应带有网络底纹。
  This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164723 51164718

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): sj13146197542@126.com

