



检验报告

TEST REPORT

中心编号(No.): 201703AW471


样品名称: B型干拌轻集料混凝土
Sample Name

委托单位: 北京博盛达装饰工程有限公司
Client
检验类别: 委托检验
Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703AW471

第1页共2页

备注:(此处	室的 生活生生生生	检验检测专用章			
	签发日期: 2017年 04 月 30 日 (極验测试章)				
检验结论	*依据标准 JGJ 51-2002 规定的试验方法进行检验,送检样品的干密度、抗压强度、导热系数的检验结果达到 12BJ1-1 中干拌复合轻集料混凝土垫层 B型(用于楼面或屋面垫层)的技术指标要求。*				
检验项目	1. 干密度 2. 抗压强度 3. 导热系数				
检验依据	JGJ 51-2002《轻骨料混凝土技术规程》 12BJ1-1《工程做法》				
样品数量	100kg	样品状态	颗粒与干粉料的 混合物		
来样日期	2017年 03月 23日	规格型号			
生产日期		样品编号			
生产单位	北京博盛达装饰工程有限公司	等级	B型		
委托单位	北京博盛达装饰工程有限公司	商标	路路路		
样品名称	B型干拌轻集料混凝土	检验类别	委托检验		

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201703AW471

第2页 共2页

序号	检验项目	标准要求 [干拌复合轻集料混 凝土垫层 B 型(用于楼 面或屋面垫层)	检验结果	单项结论
	千密度/ (kg/m³)	≤850	810	合格
2	抗压强度/MPa	≥3.0	3.1	合格
3	导热系数/[W/(m⋅K)]	≤0.25	0.22(平均温 度: 25.00℃)	合格

(以下空白)

备注: 配比: 料: 水=1.0: 0.80。

说明

Notice

1、本报告无中心"检验测试章"和骑缝章无效。

This test report is invalid without the seal.

2、本报告无"编制、审核、批准"签字无效。
This test report is invalid without the gionatures of the

This test report is invalid without the signatures of the related persons. 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>dmtc2007@163.com</u>