



# 检验报告

### TEST REPORT

中心编号(No.): 201608CW104

TIME

样品名称: Sample Name	贝壳粉生态环保涂料		
委托单位: Client	广东狮力德建材有限公司		
检验类别:	委托检验		
Test Type	<b>计算机时间可以可以</b>	3	

建筑材料工业技术监督研究中心 Technical Supervision and Research Center of the Building Materials Industry





# 建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

150002283084

## 检验报告

#### REPORT

中心编号(No.): 201608CW104

201008C W 104		第1页共2页			
贝壳粉生态环保涂料	检验类别	委托检验			
广东狮力德建材有限公司	商标	狮力德			
广东狮力德建材有限公司	等 级	一级			
	样品编号	0010			
2016年08月01日	规格型号	SLD010			
1kg	样品状态	粉状			
JC/T 1074-2008《室内空气净化功能涂覆材料净化性能》					
1. 甲醛净化效率					
10/4-2008 中 1 类材料的技术指标要求。	* : 2016年08	术监察			
	贝壳粉生态环保涂料 广东狮力德建材有限公司 广东狮力德建材有限公司 2016年08月01日 1kg JC/T1074-2008《室内空气净化功能涂 1. 甲醛净化效率 *经检验,送检样品的甲醛净化:1074-2008中1类材料的技术指标要求。	贝壳粉生态环保涂料 检验类别 广东狮力德建材有限公司 商 标			

备注: 生产批号: 201607008A。

制:

检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



## 建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

### 检验报告

TEST REPORT

中心编号(No.): 201608CW104

第2页共2页

序号	检验项目	标准要求 ( 1 类 )	检验结果	单项结论
1	甲醛净化效率 (%)	≥75	81.6	合格

(以下空白)

三月八月三

备注: (1) 配比: 粉:水=0.6:0.5;

(2) 送检样品的涂刷量: 0.6kg/m²。



#### 说明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
   This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期恕不 受理。
  - Any doubt should inform us within 15 days after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
   This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>dmtc2007@163.com</u>

