



检验报告

TEST REPORT

中心编号(No.): 201611AC002



样品名称:	轻集料混凝土连锁砌块			
Sample Name				
受检单位:Client	北京栋恒旺达建筑材料有限公司			
检验类别:	10000000000000000000000000000000000000			
Test Type				

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201611AC002

第1页 共2页

10002	ALCOHOLD ALCOHOLD	第Ⅰ贝共 4贝				
锁砌块	检验类别	抽样检验				
筑材料有限公司	生产日期	1999				
筑材料有限公司	规格型号	395mm×140mm×195mm				
招望的结	商标					
本 191	等级	MU3.5 级				
	抽样数量	20块				
	抽样基数	10000 块				
建筑材料工业干混砂浆产品质量监督检验测试中心						
GB/T 15229-2011《轻集料混凝土小型空心砌块》						
1. 密度等级 2. 抗压强度						
) 级的技术指标: 中强度等级 MU3	要求;抗压强 8.5 的技术指标 发日期:201	存合标准 GB/T 15229-201度的检验结果符合标准 要求。 6年11月14日 检验测试章)				
The state of the s						

批 核: %

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201611AC002

第2页共2页

电话: 010-51164723 邮编: 100024

序号	检验项目	标准要求 ≥810, ≤900		检验	结果	单项 结论
	密度等级/(kg/m³) (密度等级 900 级)			890		合格
	抗压强度/MPa	平均值	最小值	平均值	最小值	超起
~ (强度等级 MU3.5)	(强度等级 MU3.5)	≥3.5	≥2.8	3.6	3.4	合格工

(以下空白

备注: (此处空白)

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com