



检验报告

TEST REPORT

中心编号(No.): 201702AW278

TIME

样品名称:	聚合物粘结砂浆				
Sample Name	33433434343434343434343434343434343434				
委托单位: Client	北京绿港中维建材有限公司				
检验类别:	委托检验				
Test Type					

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201702AW278

第1页 共2页

备注:(此处	签发日期: 2017年03月 日本 全 全 全 全 全 全 全 全 全 全 全 全 全 全 全 全 全 全				
检验结论		THE ONLY COM			
認	*经检验,送检样品的拉伸粘持标准 JG 149-2003 中胶粘剂的技术指	接强度(与水泥砂浆) 标要求。*	的检验结果符合		
检验项目	1. 拉伸粘接强度(与水泥砂浆)				
检验依据	JG 149-2003《膨胀聚苯板薄抹灰外墙外保温系统》				
样品数量	20kg	样品状态	粉状		
来样日期	2017年02月28日	规格型号	干粉型		
生产日期		样品编号	朝建		
生产单位	北京绿港中维建材有限公司	等 级			
委托单位	北京绿港中维建材有限公司	商标	中拉克		
样品名称	聚合物粘结砂浆	检验类别	委托检验		

批准:

核:近郊

制: 苏亮

检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201702AW278

第2页共2页

序号	检验项目		标准要求 (股粘剂)	检验结果	单项结论
	拉伸粘接强度 (与水泥砂浆)	原强度	≥0.60	0.84	合格
	/MPa	耐水	≥0.40	0.65	合格

(以下空白)

备注: 配比: 粉:水=4:1。

や草

说一明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if crased, altered or copied partially.

对本报告若有异议,应于收到报告之口起;五个工作目内向本中心提出,逾上期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

50 委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 中果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry:
- 7、本报告采用防伪纸张,复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address)、北京市朝阳区管由东里工号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code):100024

电话(Tel):(010) 51164723 51164718

传真(Fax)。(010)5/164724

报告真伪查询(Tel)。(010) 51164716

Mth (Web), http://www.dimtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com