

TEST REPORT

中心编号(No.): 201212AW116

样品名称:

硅藻土多核高分子保温砂浆

Sample Name

委托单位: 长白县立伟硅藻土综合制品有限公司

Client

检验类别:

委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





## (国家)建筑材料工业技术监督研究中心

# 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201212AW116

第1页共2页

样品名称	硅藻土多核高分子保温砂浆	检验类别	委托检验			
委托单位	长白县立伟硅藻土综合制品有限公司	商标	文禾日			
生产单位	长白县立伟硅藻土综合制品有限公司	样品状态	颗粒与干粉料的混合物,无结块; 液状,无分层			
生产日期	2012年12月10日	生产批号				
来样日期	2012年12月14日	样品编号				
样品数量	粉料 100kg; 胶 10kg	规格型号	的是那种			
检验依据	GB/T 20473-2006《建筑保温砂浆》					
检验项目	1. 堆积密度     2. 干密度     3. 抗压强度     4. 导热系数       5. 线收缩率     6. 压剪粘结强度     7. 软化系数     8. 燃烧性能级别       9. 抗冻性     10. 放射性(放射性比活度)					
检验结论	*经检验,送检样品的堆积密度、收缩率、压剪粘结强度、软化系数、原射性比活度)的检验结果符合标准 G求。*	<ul><li>然烧性能級別、</li><li>B/T 20473-200</li><li>安日期: 200</li></ul>	抗冻性,放射性(放			

备注: (此处空白)

批准: [1]

审核: 7英四

编制:



检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



(国家)建筑材料工业技术监督研究中心 Technical Supervisions and Research Control of the Building Medicals Industry

#### (国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201212AW116

第2页 共2页

序号	检验项目		标准要求 (Ⅱ型)	检验结果	单项结论
	堆积密度/ (kg/m³)		≤350	262	合格
2	千密度/ (kg/m³)		301 ~ 400	340	合格
3	抗压强度/MPa		≥ 0.40	. 0.52	合格
4	导热系数(平均温度: 25.00℃)/(W/(m·K))		≤0.085	0.076	合格
5	线收缩率/%		≤ 0.30	0.29	合格
6	压剪粘结强度/kPa		≥ 50	98	合格
7	软化系数		≥ 0.50	0.79	合格
8	燃烧性能级别		A级	A级	合格
9	抗冻性 (15次冻 融循环)	质量损失/%	€5	4.2	合格
		强度损失/%	≤25	23	合格
10	放射性 (放射性比活度)		内照射指数 (I <sub>Ra</sub> ) ≤1.0	0.2	合格
			外照射指数 (I <sub>y</sub> ) ≤1.0	0.3	合格

(以下空白)

备注: 配比: 液体 (胶: 水=1kg: 3kg): 料=2kg: 1kg。

### 说明

#### Notice

- I、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"批准、审核、编制"签字无效。
   This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期恕不 受理。

Any doubt should inform us within 15 days after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告采用防伪纸张,复印后应带有网络底纹。
This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164723 51164718

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): sj13146197542@126.com