

# 检验报告

TEST REPORT

中心编号(No.): 201702AW044



样品名称:	外墙柔性腻子			
Sample Name				
委托单位:	北京亚邦丰利保温建材有限公司			
Client				
检验类别:	委托检验			
Test Type				

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industric Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201702AW044

第1页共2页

1 0 -10 3 (x	10.7. 201702111011		~ ~ ~ ~		
样品名称	外墙柔性腻子	检验类别	委托检验		
委托单位	北京亚邦丰利保温建材有限公司	商标	23255		
生产单位	北京亚邦丰利保温建材有限公司	等级			
生产日期	是起始起	样品编号	经经验		
来样日期	2017年02月22日/	规格型号	干粉型		
样品数量	20kg	样品状态	粉状		
检验依据	JG/T 157-2009《建筑外墙用腻子》				
检验项目	1. 初期干燥抗裂性 2. 耐水性 3. 粘结强度(标准状态)				
检验结论	*经检验,送检样品的初期干燥抗态)的检验结果符合标准 JG/T 157-200 *		的技术指标要求		
		《检验》	中子		
备注:(此处空台)工口是工品中工工品中工品中工品中工品中工品中国					

批 准:

址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

### (国家)建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201702AW044

第2页共2页

序号	检验项目	标准要求 [普通型(P)]	检验结果	单项结论
語	初期干燥抗 单道施工厚度 裂性 (6h) ≤1.5mm 的产品	1mm 无裂纹	lmm 无裂纹	符合
2	耐水性 (96h)	无异常	无异常	符合
138	粘结强度 /MPa   标准状态	≥0.60	0.75	合格

(以下空白)

备注: 配比: 粉: 水=1.0: 0.40。

检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024

#### 说明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.

7、本报告采用防伪纸张,复印后应带有网络底纹。
This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话(Tel):(010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.en/

电子邮箱 (E-mail): dmtc2007@163.com