



验搜告

TEST REPORT

中心编号(No.): 201703AW476

样品名称:

柔性耐水腻子

Sample Name

委托单位:

北京维一诺化工科技有限公司

Client

检验类别:

委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业于混砂浆产品质量监督检验测试中心

China Building Material Industry Content of Quality Supervision and Test of Dry-mixed Mortar







150002283084(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

验报告

TEST REPORT

中心编号(No.): 201703AW476

第1页共2页

1	The state of the s		
样品名称		检验类别 委托检验	
委托单位	北京维一诺化工科技有限公司	商品种种品	
生产单位	北京雞一端化工科技有限公司		
生产目期		样品编号	
来样日期	2017年03月24日	规格型号于粉型	
样品数量	20kg 20kg 20kg 20kg 20kg 20kg 20kg 20kg	样品状态。新北	
检验依据	JG/T 157-2009《建筑外墙用赋子》		
检验项目	1. 初期干燥抗裂性 2. 耐水性 3.	粘结强度(标准状态)	
全型的企业的企业。 检验结论	*经检验, 送检样品的初期干燥抗裂性态)的检验结果符合标准 JG/T 157-2009。* * * * * * * * * * * * * * * * * * *		
备注: (此处			

批

核: 光水

制治



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

验报告

TEST REPORT

中心编号(No.): 201703AW476

第2页共2页

	大大大大大大大大大大大大大大大大大大大大大大大大大大大大大大大大大大大大大	标准要求 [柔性 (R)]	检验结果	单项结论
	物期干燥机 单道卷工厚度 製性(6h) ≤1.5mm 的产品	limm 天梨飲	Imm 无裂线	

器	將對發度 MPa	0.60		

(以下空白)

备注: 配比: 粉: 水=1.0: 0.40。

说。。明

Notice

- 1、本报告无中心"检验测试章"和骑鋒章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伤纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管座东里一号北楼

No. 1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话(Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询(Tel):(010)51164716

例址 (Web): http://www.dmtc.org.cn/

电子邮箱(E-mail): dmtc2007@163.com