





TEST REPORT

中心编号(No.): 201202AW315

THAZITE

| ±± | 15 | <b>4</b> /7 | 43. |
|----|----|-------------|-----|
| T  | 1  | 称:          |     |

瓷砖粘接(翻新)砂浆

Sample Name

委托单位: 北京博奥宏达科贸有限责任公司

Client

检验类别:

委托检验

Test Type

(国家) 建筑材料工业技术监督研究中心

建筑材料工业于混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201202AW315

第1页共2页

| 样品名称 | 瓷砖粘接 (翻新) 砂浆  | 检验类别 | 委托检验    |  |  |
|------|---|------|---------|--|--|
| 委托单位 | 北京博奥宏达科贸有限责任公司  | 商标   | 宏奥      |  |  |
| 生产单位 | 北京博奧宏达科貿有限責任公司  | 样品状态 | 粉狀      |  |  |
| 生产日期 | 2012年01月  | 生产批号 | AN PARK |  |  |
| 来样日期 | 2012年02月24日   | 样品编号 |         |  |  |
| 样品数量 | 20kg  | 规格型号 | 干粉型     |  |  |
| 检验依据 | JC/T 547-2005《狗瓷墙地砖胶粘射》   |      |         |  |  |
| 检验项目 | 1. 拉伸胶粘原强度 2. 浸水后拉伸胶粘强度   |      |         |  |  |
| 检验结论 | *经检验, 送检样品的粒伸胶粘原强度、浸水后拉伸胶粘强度的检明结果符合标准 JC/T 547-2005 中普通型胶粘剂 (C1) 技术指标要求。*  签发日期: 2012 年 05 月 25 日 |      |         |  |  |

备注:(此处空台)

批准:星如麦 审核: 于其 编制: 丁》

## (国家) 建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortan

# 检验报告

TEST REPORT

中心编号(No.): 201202AW315

第2页 共2页

| 序号 | 检验项目          | 标准要求 | 检验结果 | 单项结论 |
|----|---------------|------|------|------|
|    | 拉伸胶粘原强度/MPa   | ≥0.5 | 0.8  | - 含格 |
| 2  | 浸水后拉伸胶粘强度/MPa | >0.5 | 0.5  | 合格   |

(以下空白)

备注: filk: 松: 水=4: 1.

### 说明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the scal.
- 2、木报告尤"编制、审核、批准"签字无效。 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期怨不 受理。

Any doubt should inform us within 15 days after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市初阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

南鍋 (Post Code): 100024

电话(Tel): (010) 51164723 -51164718

(th. (Fax): (010) 51164723 51164718

White (Web): http://www.dmtc.org.cn/

电子解箱 (E-mail): <u>sj13146197542@126.com</u>